



Track Ride PRODUCT SPECIFICATIONS

FITTINGS

- Aluminum alloy (GM70B) manufactured and tested in

accordance with the following ASTM Standards:

- B179-68,
- B108-68, E10-66, E8-66
- Powder coat finish
- Predrilled

SEALING GASKET

- Neoprene rubber
- 60 +/- 5 durometer hardness
- Double sided adhesive

HARDWARE

- Tamper resistant
- Special tool required for install

TRACK RIDE

- Powder coat finish
- Middle extruded section - 6063 Alumag Alloy
- Handle - 535 Alumag Alloy
- End Cap - 535 Alumag Alloy

PRETREATMENT WASH PRIMER

- 4860-420 primer / 1000-44 activator
- Polyvinyl-butyril resin based primer
- Used on all milled steel and all weld joints
- Designed to give adhesion to a wide variety of metal substrates
- Provides added metal protection against rust
- Imparts extra durability to topcoat (powder coat)

- When reduced properly, it meets the definition of a "pretreatment" primer found in many air quality regulations

POWDER COAT FINISH

- TGIC Polyester
- Electrostatic application
- Baked-on @ 400 degrees
- 5-7 mills thick
- Lead free
- High gloss
- No peel / No flake finish
- Resistant to salt spray (ASTM B117)
- Resistant to humidity (ASTM D2247)
- Direct/Indirect impact 120 in. pounds (ASTM D2794)
- Good to excellent resistance to most solvents, oils, acids and alkalies

**DunRite
Playgrounds**

(888) 882-1929

www.dunriteplaygrounds.com
sales@dunriteplaygrounds.com